

HYDROXYAPATITE (HAp) BIOCERAMICS MADE FROM THE *Celetaiya persclupta* SNAIL SHELLS FROM POSO LAKE

Aqung Rimayanto Gintu^{1,*}, Elizabeth Betty Elo Kristiani², and Yohanes Martono³

¹Magister Biology, Faculty of Biology, Satya Wacana Christian University
Jl. Diponegoro No. 52-60 Salatiga, Central Java 50711, Indonesia

²Faculty of Biology, Satya Wacana Christian University
Jl. Diponegoro No. 52-60 Salatiga, Central Java 50711, Indonesia

³Faculty of Science and Mathematics, Satya Wacana Christian University
Jl. Diponegoro No. 52-60 Salatiga, Central Java 50711, Indonesia

* Correspondence: Telp : 082138094517, email: aguggintu911@gmail.com

Received: November 25, 2020

Accepted: December 26, 2020

Online Published: December 31, 2020

DOI : [10.20961/jkpk.v5i3.45983](https://doi.org/10.20961/jkpk.v5i3.45983)

ABSTRACT

Bioceramic Hydroxyapatite (HAp) was a derivated chemical synthetic compound from calcium phosphate commonly used to care for hard tissue damage. Bioceramic Hydroxyapatite can be synthesized from the compounds rich with calcium contains. This study treated the synthesis and physicochemical Characterization of the HAp made from *Celetaiya persclupta* snail shells obtained from Poso lake. From the characterization of the sample *C. presclupta* shells obtained the water contains $0.50 \pm 0.00\%$; ash contains $0.9913 \pm 0.0017\text{g/g}$; potassium $0.0005 \pm 0.00007\text{g/g}$; calcium $0.0391 \pm 0.0059\text{g/g}$; phosphate $0.0221 \pm 0.0009\text{g/g}$; phosphorus 0.0111 ± 0.0005 and the ratio of Ca/P $1.7382 \pm 0.1994\%$. The synthesis of HAp by base precipitation method showed the yield of synthesis $85.2891 \pm 4.2496\%$ with the level of material reduction during synthesis $18.0442 \pm 1.1684\%$. The result of characterization of the HAp showed that the potassium contains $0.0002 \pm 0.00003\text{g/g}$; calcium $0.0121 \pm 0.0031\text{g/g}$; phosphate $0.0167 \pm 0.0013\text{g/g}$; phosphorus $0.0084 \pm 0.0007\text{g/g}$; ratio of Ca/P $1.3724 \pm 0.2736\%$; porosity $9.9929 \pm 0.7626\%$; swelling ability $24.8416 \pm 1.4989\%$; and biodegradability $10.8958 \pm 1.1781\%$. The overall results concluded that the *C. presclupta* snail shells could become a source of Bioceramic Hydroxyapatite (HAp).

Keywords: bioceramics, HAp, molluscan shells

INTRODUCTION

Hydroxyapatite (HAp) was a synthetic compound derivated from calcium (Ca) have chemical name $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$ [1]; ratio of Ca/P 1.67; density 3.19g/ml [2]; room symmetric P63/m; side parameters $a = 9.432\text{Å}$, $c = 6.875\text{Å}$ and hexagonal crystal system [3]. HAp is very popular in medic, mainly because the biocompatible characteristic can replace the pen (Platina) to manage bone

fracture [4]. The Chemical structure of HAp potentially uses as remineralization compounds because they have similarity with the calcium structure build the bones [5]. The HAp can be synthesized from the materials rich with calcium contains and commonly, the HAp composite apply to repairing the fractured bone and patch the tooth [5]. The chemical structure of HAp showed in Figure 1.




Figure 1. The Chemical Structure of HAp [6,7]

The hydroxyapatite was a product of the modification structure of calcium carbonate (CaCO_3), so it can be synthesized from the rich calcium contain materials [1,4,5]. Another synthesis research before in Indonesia used several kinds of calcium source as cow bones [3,8], Molluscan shells [9,10], eggshells [11,12,13,14], Ca and P ions in bacterial cellulosic membranes [15], and calcite [16].

The Molluscan shells can apply as HAp sources because they have higher calcium than eggshells [9,10]. The application of clamshells as HAp scorches conceived because of Indonesia's large abundance was potential: 34.929 tons per year where the blood clams as the main commodity [9]. The blood clams shells containing 98.7% of calcium (Ca) and 0.002% phosphor (P) [17]. Another research before threatened the synthesis of HAp from shellfish (*polymesoda erosa*) reported that the stirring time would increase the synthesis result of HAp [18].

The mainly Molluscan shells used as a source of HAp were clamshells (marine or lacustrine clams) [9,17,18], but still rare for the snail shells [10], so this study treated the synthesis of HAp from *Celetaiya persclupta* snail shells obtained from Poso Lake, Central of

Sulawesi. Those shells were chosen as HAp source because they predicted it has large calcium can be synthesized became HAp. The abundance of the empty shells is large and easy to find in large amounts along the lakeshore (on and below the sand). Those shells didn't manage yet and free to take for now. Sometimes just take away by the tourists as merchandises. The HAp synthesized from *C. persclupta* shells will be conceived as a reparing compound (implant, grafting, filer) to the hard tissues.

METHODS

1. Research Locations

The *C. persclupta* snail shells were obtained from Poso Lake, Central of Celebes, Indonesia. The synthesis and chemical characterization of HAp from its shells were treated in the Base Chemical Laboratory of Faculty of Science and Mathematics, Satya Wacana Christian University, Salatiga Central Java.

2. The Shells Characterization

The *C. persclupta* shells' chemical characterization included water contains, ash, organics, carbons, and silicon by gravimetric [19]. The Phosphor has measurements by UV-Vis Spectrophotometer and HACH photometer, calcium measured twice by titrimetric [19] and UV-Vis Spectrophotometer [16], also the potassium and sulfur by HACH photometer.

3. Synthesis of HAp from *C. presclupta* Shells

The synthesis of HAp from *C. presclupta* shells using base precipitation method [1,14].

4. The Chemical Characterization of HAp

The chemical characterization of the HAp from *C. persclupta* shells included the Phosphor contains measurements by UV-Vis Spectrophotometer and HACH photometer, calcium measured twice by titrimetric [19] and UV-Vis Spectrophotometer [20], also the potassium and sulfur by HACH photometer.

5. The Biochemical Characterization of HAp

The biochemical Characterization of the HAp from *C. persclupta* shells included the Porosity, Biodegradability, and Swelling Ability measurements by gravimetric [21,22,23].

RESULTS AND DISCUSSION

The *C. persclupta* snail was one of the endemic molluscan species in Poso Lake [24], Central of Sulawesi. It's easy to find those shells in large amounts on the lakeshore, in the water, or along the Poso River. Those shells already empty then push by the rush stream or the waves to the sands on the lakeside. Those shells were containing calcium to build and strengthen the shell's structure. Genetically, the calcium synthesis in the snails' body is very high because the

contains of fat and proteins in another side is used to maintain the snails' body temperature in the water. After those snails die, their shells left can be utilized if calcium contains. But in shell form, the calcium still bonds with silicon, so it can't be used immediately. The calcium from *C. persclupta* shells can be processed hydroxyapatite (HAp) bioceramics after separated from the organics and silicones. The *C. presclupta* shells showed in Figure 2.



Figure 2. The *C. persclupta* Shells (Personal Documentation)

The source of HAp needs to be characterized to ensure the existence of calcium and phosphorus [5,11], so the chemical characterization treated to the *C. persclupta* shells before synthesized to HAp. The result of Characterization showed in Table 1.

Table 1. The Result of Characterization of the *C. persclupta* Shells

Methods	Contains	Units	Result
Gravimetric	Water	%	0.50 ± 0.00
	Ash	g/g	0.9913 ± 0.0017
	Organics	g/g	0.0103 ± 0.0018
	Carbon (C)	g/g	0.0060 ± 0.0011
	Silicon (Si)	g/g	0.1186 ± 0.0054
	Silicate (SiO)	g/g	0.2317 ± 0.0045
Titrimetric	Calcium (Ca)	g/g	0.0518 ± 0.0001
Spectrophotometric	Calcium (Ca)	g/g	0.0391 ± 0.0059
	Sulphate (SO ₄)	g/g	0.0036 ± 0.0005
	Potassium (K)	g/g	0.0005 ± 0.00007
	Phosphate (PO ₄)	g/g	0.0221 ± 0.0009

HACH Photometer	P ₂ O ₅	g/g	0.0035 ± 0.0001
	P ₂ O ₅ Dissolved	g/g	0.0017 ± 0.00007
	P ₂ O ₅ Total	g/g	0.0051 ± 0.0002
	Phosphor (P) Dissolved	g/g	0.0022 ± 0.0001
	Phosphor (P) Total	g/g	0.0111 ± 0.0005
	The ratio of Ca/P (B)	%	1.7382 ± 0.1994
	Phosphate (PO ₄)	g/g	0.0085 ± 0.00007
	P ₂ O ₅	g/g	0.0064 ± 0.00007
	Total Phosphor (P) (490)	g/g	0.0028 ± 0.00003
	Total Phosphor (P) (496)	g/g	0.0045 ± 0.00007
The ratio of Ca/P (O)		%	2.24 ± 0.55

In the molluscan shells, Calcium was not immediately in HAp form but CaCO₃ (Calcium Carbonate) and Ca₂PO₄ (Calcium Phosphate) [9,10,17,18], in which those compound have fragile structure and can't be applied as bioceramics, especially to propping.

The chemical characterization treated to the *C. persclupta* shells showed in Table 1 strengthens the hypothesis because those shells contain the minerals needed in the HAp synthesis process. Based on Table 1 also can be predicted that the *C. persclupta*

shells potentially produced three kinds of Apatite Bioceramics, that is Hydroxyapatite (HAp) with chemical structure Ca₁₀(PO₄)₆(OH)₂ [1,4,5], Carbonate Apatite (Cap) with chemical structure Ca₁₀(PO₄)₆(CO₃)₃(OH)₂ (Dahlite) and Ca₁₀(PO₄)₆CO₃ (Pedolite) [25]. The study of HAp as remineralization agents to the hard tissues already exist in Indonesia used another potentially compound as HAp source. The potentiality comparison of *C. persclupta* shells with the references from other research showed in Table 2.

Table 2. The Potentiality Comparison of *C. persclupta* Shells With the References from Another Research

Minerals	<i>C. persclupta</i> Shells	References			
		[11]	[13]	[17]	[14]
Ca	0.0391 ± 0.0059g/g	0.0188±0.0007 g/g	67.22%		
		0.0195±0.00 g/g	73.75%	98.7%	76.6%
K	0.0005 ± 0.0001g/g	-	-		4.20%
	0.0221 ± 0.0009g/g	0.001349 g/g	71.23%		
PO ₄		0.001355 g/g	78.62%	-	-
		0.001294 g/g	-		
P	0.0111 ± 0.0005g/g	-	-	0.02%	-

The comparison showed in Table 3 concluded that the *C. persclupta* shells with those minerals have the same potentiality levels to become a HAp source. Because the potentiality of Ca and P contains then proces-


sed the synthesis of *C. persclupta* shells to HAp using base precipitation methods. The result of chemical and biochemical Characterization of the HAp from *C. persclupta* shells showed in Table 3.

Table 3. The Result of Chemical and Biochemical Characterization to the HAp from *C. persclupta* Shells

Methods	Synthesis Parameters	Units	Result
Gravimetric	Rendement	%	18.0442 ± 1.1684
	Yield	%	85.2891 ± 4.2496
Mineral Contains			
Titrimetric	Calcium (Ca)	g/g	0.0152 ± 0.00005
	Calcium (Ca)	g/g	0.0121 ± 0.0031
	Sulphate (SO ₄)	g/g	0.0009 ± 0.0001
	Potassium (K)	g/g	0.0002 ± 0.00003
	Phosphate(PO ₄)	g/g	0.0167 ± 0.0013
Spectrophotometric	P ₂ O ₅	g/g	0.0027 ± 0.0002
	P ₂ O ₅ Dissolved	g/g	0.0013 ± 0.0001
	P ₂ O ₅ Total	g/g	0.0039 ± 0.0003
	Phosphor (P) Dissolved	g/g	0.0017 ± 0.0001
	Phosphor (P) Total	g/g	0.0084 ± 0.0007
	The ratio of Ca/P (B)	%	1.3724 ± 0.2736
	Phosphate (PO ₄)	g/g	0.0040 ± 0.0000
HACH Photometer	P ₂ O ₅	g/g	0.0030 ± 0.0000
	Total Phosphor (P) (490)	g/g	0.0013 ± 0.0000
	Total Phosphor (P) (496)	g/g	0.0029 ± 0.00007
	The ratio of Ca/P (O)	%	1.33 ± 1.32
Biochemical Parameters			
Gravimetric	Porosity	%	9.9929 ± 0.7626
	Biodegradability	%	10.8958 ± 1.1781
	Swelling Ability	%	24.8416 ± 1.4989
Qualitative Observation			
Direct Observation	Texture	-	Soft
	Shape	-	Powder
	Color	-	White

In this study, the HAp synthesis process using the base precipitation method with the incandescent temperature 900°C in 3 hours. In this incandescent temperature, confirmed the Carbon atoms and compounds (C and CO_x) then difficult to confirm the product of another kind of apatite bioceramic like Cap [25], because carbon will be incandescent at 600°C [19] so can conclude that the apatite bioceramic produced in this process was Hydroxyapatite (HAp) [1]. Another kind of bioceramic based on Potassium (K) is difficult to confirm because potassium contains very small measurements. It was 0.0005±0.00007g/g.

Along the synthesis process of HAp from molluscan shells, the chemical reaction to occurs showed in [Equation 1](#):



The HAp synthesis using base precipitation showed the level of potential for success was 85.2891±4.2496%. The reduction of mass material reduction level was 18.0442±1.1684%, which showed that the *C.persclupta* shells potentially to became a source of HAp. The comparison of the result of HAp synthesis from *C. persclupta* shells with the references showed in [Table 4](#).

Table 4. The Comparison of the Result of HAp Synthesis from *C.persclupta* Shells with the References

Result	HAp from <i>C. persclupta</i> shells	References		
		[26]	[18]	[14]
% Rendement (w/w)	85.2891 ± 4.2496	73.75	53 60 71	-
% Mass Reduction (Yield)	18.0442 ± 1.1684	-	-	36 64

The Visibility of HAp synthesized from *C. persclupta* shells comparing with the HAp from another source showed in Figure 3. The measurement of Calcium contains to HAp need for the applicative and scientific reasons. It is necessary to report the Ca and P containing remineralization, reparations, or filer compounds for application purposes. Measurement of Ca and P content to compare the synthesis process's efficiency and effectiveness from various HAp methods and sources. Each synthesis method causes a reduction in the mass of the source, so it is necessary to study in-depth methods with minimal mass reduction, but the Ca and P content is still in the standard range for HAp. The comparison of mineral contains in HAp showed in Table 5.




Figure 3. The Visibility of HAp synthesized from *C.persclupta* shells comparing with the HAp from another source, a HAp from *C.persclupta* shells, b and c from eggshells [11,13] by precipitation, d from eggshells [11] by hydrolysis, e from Cow Bones [8].

Table 5. The Comparison of Mineral Contains in HAp

Minerals	HAp from <i>C. persclupta</i> Shells	References	
		[14]	[8]
Ca	$0.0121 \pm 0.0031\text{g/g}$	9.78; 10.50% (atom)	88.88
PO ₄	$0.0167 \pm 0.0013\text{g/g}$	-	-
P	$0.0084 \pm 0.0007\text{g/g}$	9.35; 8.97% (Atom)	8.78

Another parameter for the Ca and P measurement contains the ratio of calcium against phosphor (Ca/P). According to the

references, the common ratio Ca/P of HAp was 1.6%. The comparison of the ratio Ca/P from synthesized HAp showed in Table 6.

Table 6. The Comparison of the Ratio Ca/P from Synthesized HAp

Parameter	HAp from C. <i>persclupta</i> Shells	References					
		[13]	[27]	[2]	[15]	[9]	[14]
Ratio Ca/P (%)	1.3724 ± 0.2736 (B)	1.07	1.66	1.67	1.6760	1.60	0.67
	1.33 ± 1.32 (O)	1.06	1.74		1.8209	1.67	1.67
			1.88		0.0433	1.74	2.67
			1.78		0.0599		
					0.0423		

Table 5 concluded that HAp synthesized from *C. persclupta* shells was still in the range of Ca/P's referenced ratio of Ca/P. The ratio of Ca/P connected to the particle size, the ratio of Ca/P 1.57-2.67%, can reduce the particle size to ±59nm, increasing Ca/P following by reducing the particle size [14].

The next steps threatened the biochemical Characterization of the HAp from *C.persclupta* shells; the Characterization included porosity, biodegradability, and swelling ability. The comparison between the HAp from *C. persclupta* against the references showed in Table 7.

Table 7. The Comparison Between the HAp From *C.persclupta* Against the References

Parameters	HAp from <i>C. persclupta</i> Shells	References	
		[27]	[23]
Porosity (%)	9.9929 ± 0.7626	88.442	
		84.890	63.7476 ± 5.79145
		74.830	
		63.906	
Biodegradability (%)	10.8958 ± 1.1781	-	27.8833 ± 0.46448
Sweling (%)	24.8416 ± 1.4989	-	10.9983 ± 7.36003

The porosity measurements aim to predict porous in the HAp as the approach when the HAp applies to the livings. The porous important as the vessel of interactives between the mineral to the cells of hard tissues. The porous was the place where the new bone cells were produced [16,27,28]. It is easy to apply the porosity HAp to the hard tissues. A large amount of porosity can cause the structure of HAp to become fragile. But in nanoscale, the large amount of porosity didn't give a fragile effect to the HAp [23], the Ca / P ratio of porous HAp to approximate the predicted physical strength of HAp when applied to living things. [21,22,23,26,28].

The measurements of biodegradability level aim to predict the decomposition of the HAp when it is applied. But the result is still preconceived if the degradability level was high, which means the HAp has a fragile structure [21,22,23].

The swelling ability measurement aims to predict the change of mass, volume, and density of the HAp when exposed to the body's chemical compound, mostly water, salt, and glucose. The response reaction, especially with the liquid compounds, will cause the bioceramic's porous binding or absorption reaction and increase its mass and volume. In the following condition, the

bioceramic structure became fragile because the liquids stuck inside the porous [21,22].

Synthetic materials derived from bone graft, bone filler, and bone-implant based on HAp due to the limited availability of bone donors but the large need [1,4,5,14]. For example, the Doktor Soetomo Surabaya hospital manages 300-400 surgical bone cases every month, then caused an increase of bone-implant materials requests [29]. On the other side, Indonesia also a country with the highest fracture sufferers in Asia [29].

CONCLUSION

The *Celetaia persclupta* snail shells potentiality to became a source of HAp for the medical needs mainly to repairing the hard tissues (*filler, grafting, implant*) based the report of the measurements of minerals contains in the shells like calcium (Ca) and phosphor (P). The mass yield from the synthesis process showed significant results. The synthesis using the alkaline precipitation method resulted in a white HAp powder indicating that the HAp from the shell of *C. persclupta* has the potential to be applied medically as a remineralizing agent in hard tissue.

REFERENCES

- [1] M. Mittal, S. Prakash, K. S. Nath, and K. P. Sapra, *Preparation Methodology of Hydroxyapatite Powder*. Departement of Metallurgical and Materials, Indian Institute of Technology, 2011.
[Google Scholar](#)
- [2] M. P. Ferraz, F. J. Monteiro, and C. M. Manuel, "Hydroxyapatite nanoparticles: A review of preparation methodologies. *Journal of Applied Biomaterials and Biomechanics*, vol. 2, no. 2, pp.74-80, 2004.
[DOI: 10.1177/228080000400200202](https://doi.org/10.1177/228080000400200202)
- [3] M. Mozafari, L. Chandrasena, I. McKenzie, K. Samedov, and P. W. Percival, "Investigation of H atom and free radical behaviour in clathrate hydrates of organic molecules". *Radiation Physics and Chemistry*, 168, 108532, 2020.
[DOI:10.1016/j.radphyschem.2011.10.006](https://doi.org/10.1016/j.radphyschem.2011.10.006)
- [4] R. A. Ramli, R. Adnan, M. A. Bakar, and S. M. Masudi, "Synthesis and Characterisation of Pure Nanoporous Hydroxyapatite." *Journal of Physical Science*, vol. 22, no. 1, pp. 25-37. 2011.
[Google Scholar](#)
- [5] D. S. R. Krishna, A. Siddharthan, S. K. Seshadri, and T. S. Kumar, "A novel route for synthesis of nanocrystalline hydroxyapatite from eggshell waste". *Journal of Materials Science: Materials in Medicine*, vol. 18, no. 9, pp. 1735-1743, 2007.
[DOI:10.1007/s10856-007-3069-7](https://doi.org/10.1007/s10856-007-3069-7)
- [6] K. Agrawal, G. Sigh, D. Puri, and S. Prakash, "Synthesis and Characterization of Hydroxyapatite Powder by Sol-Gel Method for Biomedical Application. *Journal Of Minerals and Materials Characterization and Engineering*. vol. 10, no. 8, pp. 727-734, 2011.
[DOI: 10.4236/jmmce.2011.108057](https://doi.org/10.4236/jmmce.2011.108057)
- [7] A. Elkayar, Y. Elshazly and M. Assaad, "Properties of Hydroxyapatite from Bovine Teeth." *Bone and Tissue Regeneration Insights*, 2009.
[DOI: 10.4137/BTRI.S3728](https://doi.org/10.4137/BTRI.S3728)
- [8] I. Wahdah, S. Wardhani, and Darjito. "Sintesis Hidroksiapatit dari Tulang Sapi dengan Metode Basa-Pengendapan." *Kimia Student Journal* vol. 1, no. 1, pp. 92-97, 2014.
[Google Scholar](#)
- [9] Affandi, A. Amri, and Zultiniar, "Sintesis Hidroksiapatit dari Cangkang Kerang Darah (Anadara granosa) dengan proses Hidrotermal Variasi Rasio Mol Ca/P dan Suhu Sintesis." *Jom FTEKNIK*, vol. 2, no. 1, pp. 1-8, 2015.
[Google Scholar](#)
- [10] I. H. Suparto, and D. K. Putri, "Synthesis of hydroxyapatite from rice fields snail shell (*Bellamya javanica*) through wet method and pore

- modification using chitosan". *Procedia Chemistry*, vol. 17, pp. 27-35,2015.
DOI:10.1016/j.proche.2015.12.120
- [11] A. R.Gintu, E. B. E. Kristiani, and Y. Martono,"Biokeramik Hidroksiapatit (HAp) Berbahan Dasar Cangkang Tiram Anodontia nuttaliana dari Danau Poso". *Eksperi*, vol. 17, no. 2, pp. 86-92, 2020.
DOI:10.31315/e.v17i2.3758
- [12] Mahreni, E. Sulistyowati, S. Sampe, and W. Chandra, "Pembuatan Hidroksiapatit dari Kulit Telur." Pengembangan Teknologi Kimia untuk Pengolahan Sumber Daya Alam Indonesia. Yogyakarta, 2012.
[Google Scholar](#)
- [13] I. A. Suci, and Y. D. Ngapa, "Sintesis dan Karakterisasi Hidroksiapatit (HAp) dari Cangkang Kerang Ale-Ale Menggunakan Metode Presipitasi Double Stirring". *CAKRA KIMIA (Indonesian E-Journal of Applied Chemistry)*, vol. 8, no. 2, pp. 73-81, 2020.
[Google Scholar](#)
- [14] N. S. Wardani, A. Fadli, and Irdoni, "Sintesis Hidroksiapatit dari Cangkang Telur dengan Metode Presipitasi." *JOM FTEKNIK*, vol. 2, no.1, pp. 1-4, 2015.
[Google Scholar](#)
- [15] T. Windarti, and Y. Astuti, "Pengaruh Konsentrasi Ca²⁺ dan (PO₄)₃₋ pada Pembentukan Hidroksiapatit di dalam Matriks Selulosa Bakterial," *Jurnal Kimia Sains dan Aplikasi*, vol. 9, no. 3, pp. 60-64, Dec. 2006.
DOI: 10.14710/jksa.9.3.60-64
- [16] I. Wadu, H. Soetjipto, and M. N. Cahyanti, "Characterization and Antibacterial Activity Test of Hydroxyapatite (HAp) from Chicken Eggshell against Lactobacillus acidophilus Bacteria". *JKPK (Jurnal Kimia dan Pendidikan Kimia)*, vol. 2, no. 3, pp. 145-151, 2018.
DOI: 10.20961/jkp.v2i3.11862
- [17] M. Khoirudin, Yelmida and Zultiniar. "Sintesis dan Karakterisasi Hidroksiapatit (HAp) dari Kulit Kerang Darah (Anadara granosa) dengan Proses Hidrotermal." *JOM FTEKNIK*, vol. 2, no.2, pp. 1-8, 2015.
[Google Scholar](#)
- [18] R. P. Ningsih, N. Wahyuni, and L. Destiarti. "Sintesis Hidroksiapatit dari Cangkang Kerang Darah (Polymesoda erosa) dengan Variasi Waktu Pengadukan." *Jurnal Kimia Khatulistiwa*, vol. 3, no. 1, pp. 22-26, 2014.
[Google Scholar](#)
- [19] Sulaeman, Suparto, and Evianti, Analisis Kimia Tanah, Tanaman, Air dan Pupuk. Bogor. Balai Penelitian Tanah Departemen Pertanian, 2005.
[Google Scholar](#)
- [20] W. S. Rahayu, P. I. Utami and A. Kurniawati, "Validitas Penetapan Kadar Kalsium dalam Sediaan Tablet Multivitamin Secara Spektrofotometri Ultraviolet-Visible." *Jurnal Pharmacy*, vol. 8, no. 2, pp. 34-41, 2011.
[Google Scholar](#)
- [21] D. A. Wahl and J. T. Czernuszka, "Collagen-Hydroxyapatite Composites For Hard Tissues Repair". *Eur Cell Mater.*, vol. 28, no. 11, pp. 43-56, 2006.
DOI: 10.22203/ecm.v011a06
- [22] W. Wattanutchariya and W. Changkowchai, "Characterization of Porous Scaffold from Chitosan-Gelatin/ Hydroksiapatite for Bone Grafting." *IMECS. Hongkong*. 2014.
[Google Scholar](#)
- [23] A. R. Gintu, I. Wadu, M. W. Salenussa and S. Hartini, "Karakterisasi Fisikokimia Biokeramik Campuran HA_p-Kitosan". *Prosiding SNSE IV UPGRIS*, 2017.
[Google Scholar](#)
- [24] C. Gagel, "Die Beweise für eine mehrfache Vereisung Norddeutschlands in diluvialer Zeit". *Geologische Rundschau*, 4(5-6), pp. 319-362, 2013.
DOI:10.1007/BF01785981
- [25] S. V. Dorozhkin, "Dissolution mechanism of calcium apatites in acids: A review of literature". *World journal of methodology*, vol. 2, no. 1, p. 1, 2012.
DOI:10.5662/wjm.v2.i1.1

- [26] Saleha, M. Halik, N. Annisa, Sudirman, and Subaer, "Sintesis dan Karakterisasi Hidroksiapatit dari Nanopartikel Kalsium Oksida (CaO) Cangkang Telur untuk Aplikasi Dental Implan." Prosiding pertemuan Ilmiah XXIX HFI Jateng & DIY, Yogyakarta 25 April 2015. ISSN: 0853-0823, 2015.
[Google Scholar](#)
- [27] E. Kolanthai, K. Ganesan, M. Epple, and S. N. Kalkura, "Synthesis of nanosized hydroxyapatite/agarose powders for bone filler and drug delivery application". *Materials Today Communications*, vol. 8, pp. 31-40, 2016.
DOI: [10.1016/j.mtcomm.2016.03.008](https://doi.org/10.1016/j.mtcomm.2016.03.008)
- [28] A. Rahmawati, N. I. Ilmi, H. Setyawan, and S. Affandi, "Sintesis Hydroxyapatite Berukuran Nano dengan Metode Elektrokimia Menggunakan Pulse Direct Current (PDC) sebagai Bioimplant Tulang dan Gigi." *Jurnal Teknik POMITS*, vol. 1, no.1, pp. 1-4, 2012.
[Google Scholar](#)
- [29] E. P. N. Susanto, Amiatun, and D. Hikmawati. "Sintesis dan Karakterisasi Paduan Kobalt dengan Variasi Cr Melalui Metode Peleburan sebagai Material Implan." *Jurnal Fisika dan Terapannya*, vol. 2, no. 2, 2014.
[Google Scholar](#)